



Characteristics	Mirage Classic		
	Natural Collection		
Description	<ul style="list-style-type: none"> Solid prefinished hardwood flooring with tongues and grooves Micro-V bevel (on 4 sides) 		
Thickness	3/4" (19 mm)		
Length	Random lengths (from 10" (250 mm) to 76" (1,930 mm))		
Width	2-1/4" (57 mm)	2-1/2" (64 mm) and 3-1/4" (83 mm)	4-1/4" (108 mm)
Species	4 species: Maple, Yellow Birch, Red Oak, American Walnut		
Grade	<ul style="list-style-type: none"> Select & Better (Selection of more uniform wood grain with slight variations in natural shading) Exclusive (As found in nature. A complete species color and character range) 		
Color choice (refer to 2016 Mirage Collections)	1 color: Natural Some products may not be available. Ask your Mirage representative or consult the product chart.		
Finish	<ul style="list-style-type: none"> Nanolinx HD™: Finishing system made of aluminum oxide and nanosilica particle composites suspended in UV cured polyurethane. Semi-gloss (50% gloss) or Cashmere®* (18% gloss) 		
	UV Protection: All products		Formaldehyde: Free
	Water and solvent: No trace		
	Static Friction Coefficient (ASTM-D-2047): Slippery resistance of 0.5 to 0.55		
Applicable standards	Surface Burning (ASTM-E-84): <ul style="list-style-type: none"> FSI (Flame Spread Index) 100 to 150 Classe C (depends on wood species) SD (Smoke Development) 75 to 400 (depends on wood species) 		Surface Burning (ULC-S-102-2): <ul style="list-style-type: none"> FSC (Flame Spread Classification) 100 to 150 (depends on wood species) SD (Smoke Development) 200 to 300 (depends on wood species)
	Critical radiant flux (ASTM-E-648-94a): 0.25 to 0.40 watt/cm ² (depends on wood species)		R value: R 0.6 to 0.8 (depends on wood species)
	Formaldehyde emission (ASTM-E-1333-02): <ul style="list-style-type: none"> Less than 0.01 ppm 		Total VOC (ASTM-D-6670-01): <ul style="list-style-type: none"> 0.003 ppm (depends on wood species)
	Installation: Nailed or stapled down (above and on grade)		
Subfloor	Wood		
Provenance	Made in St-Georges, Qc, Canada.		
Certification	FSC® available on Maple, Red Oak and Yellow Birch.		
Use	Residential or light commercial		
Accessory	Round Stair nosing, Square Stair nosing, Round reducer, Multifunction reducer, Threshold, "T" molding, Quarter round		
Warranty	<ul style="list-style-type: none"> Structural lifetime limited warranty 35-year finish warranty for residential applications 		<ul style="list-style-type: none"> 3-year finish warranty for light commercial applications
Packaging	2-1/4" (57 mm)	2-1/2" (64 mm) and 3-1/4" (83 mm)	4-1/4" (108 mm)
Content of a box	• 20 ft ² (1,858 m ²)	• 20 ft ² (1,858 m ²)	• 18 ft ² (1,672 m ²)
Size of a box	• 86" L x 9-1/2" W x 3-1/4" H	• 79" L x 10-1/2" W x 3-1/4" H	• 82" L x 9" W x 3-1/4" H
Weight of a box	• 49 to 53 lbs	• 49 to 60 lbs	• 49 to 51 lbs
Content of a pallet	• 48 boxes = 960 ft ²	• 48 boxes = 960 ft ²	• 48 boxes = 864 ft ²
	(4 boxes/W x 12 boxes/H)	(4 boxes/W x 12 boxes/H)	(4 boxes/W x 12 boxes/H)
Size of a pallet	• 86" L x 38" W x 43" H	• 79" L x 42" W x 43" H	• 82" L x 38" W x 43" H
Relative species hardness			
NWFA Janka Test	• American Walnut	1,010 lbs - 22% softer	
Hardness test (ASTM-D-143)	• Yellow Birch	1,260 lbs - 2% softer	
	• Red Oak	1,290 lbs - average hardness	
Red Oak 1290 lbs* - 100%	• Maple	1,450 lbs - 12% harder	
*lbs = Applied force in pounds			

* Cashmere is a registered trademark used under license.