



Characteristics	Mirage Classic		
	Admiration Collection		
Description	<ul style="list-style-type: none"> <li>Solid prefinished hardwood flooring with tongues and grooves</li> <li>Micro-V bevel (on 4 sides)</li> </ul>		
Thickness	3/4" (19 mm)		
Length	<ul style="list-style-type: none"> <li>Random lengths (from 10" (250 mm) to 76" (1,930 mm))</li> </ul>		
Width	2-1/4" (57 mm)	2-1/2" (64 mm) and 3-1/4" (83 mm)	4-1/4" (108 mm)
Species	4 species: Maple, Yellow Birch, Red Oak, Knotty Walnut		
Grade	<ul style="list-style-type: none"> <li>Exclusive (As found in nature. A complete species color and character range)</li> <li>Knotty Walnut (These floors are appreciated for their pronounced color variations. They feature mineral streaks, sound and repaired knots, surface holes, pith, hairline surface cracks, and natural imperfections)</li> </ul>		
Color choice (refer to 2016 Mirage Collections)	27 colors: Nordic, Rio, Greystone, Platinum, Charcoal, Graphite, Sambuca, Java, Coffee, Waterloo, Vienna, Bolton, Umbria, Havana, Newport, Rich Oak, Colorado, Savanna, Hudson, Sonora, North Hatley, Sierra, Golden, Windsor, Nevada, Auburn, Canyon Some products may require a minimum quantity or may not be available. Ask your Mirage representative or consult the product chart.		
Finish	<ul style="list-style-type: none"> <li>Nanolinx HD™: Finishing system made of aluminum oxide and nanosilica particle composites suspended in UV cured polyurethane.</li> <li>Semi-gloss (50% gloss) or Cashmere®* (18% gloss)</li> </ul>		
	UV Protection: All products		Formaldehyde: Free
	Water and solvent: No trace		
	Static Friction Coefficient (ASTM-D-2047): Slippery resistance of 0.5 to 0.55		
Applicable standards	<b>Surface Burning (ASTM-E-84):</b> <ul style="list-style-type: none"> <li>FSI (Flame Spread Index) 100 to 150                             <ul style="list-style-type: none"> <li>Classe C (depends on wood species)</li> </ul> </li> <li>SD (Smoke Development) 75 to 400 (depends on wood species)</li> </ul>		<b>Surface Burning (ULC-S-102-2):</b> <ul style="list-style-type: none"> <li>FSC (Flame Spread Classification) 100 to 150 (depends on wood species)</li> <li>SD (Smoke Development) 200 to 300 (depends on wood species)</li> </ul>
	<b>Critical radiant flux (ASTM-E-648-94a):</b> 0.25 to 0.40 watt/cm <sup>2</sup> (depends on wood species)		R value: R 0.6 to 0.8 (depends on wood species)
	<b>Formaldehyde emission (ASTM-E-1333-02):</b> <ul style="list-style-type: none"> <li>Less than 0.01 ppm</li> </ul>		<b>Total VOC (ASTM-D-6670-01):</b> <ul style="list-style-type: none"> <li>0.003 ppm (depends on wood species)</li> </ul>
Installation	Nailed or stapled down (above and on grade)		
Subfloor	Wood		
Provenance	Made in St-Georges, Qc, Canada.		
Certification	FSC® available on Maple, Red Oak and Yellow Birch.		
Use	Residential or light commercial		
Accessory	Round Stair nosing, Square Stair nosing, Round reducer, Multifunction reducer, Threshold, "T" molding, Quarter round		
Warranty	<ul style="list-style-type: none"> <li>Structural <b>lifetime</b> limited warranty</li> <li>35-year finish warranty for residential applications</li> </ul>		<ul style="list-style-type: none"> <li>3-year finish warranty for light commercial applications</li> </ul>
Packaging	2-1/4" (57 mm)	2-1/2" (64 mm) and 3-1/4" (83 mm)	4-1/4" (108 mm)
Content of a box	• 20 ft <sup>2</sup> (1.858 m <sup>2</sup> )	• 20 ft <sup>2</sup> (1.858 m <sup>2</sup> )	• 18 ft <sup>2</sup> (1.672 m <sup>2</sup> )
Size of a box	• 86" L x 9-1/2" W x 3-1/4" H	• 79" L x 10-1/2" W x 3-1/4" H	• 82" L x 9" W x 3-1/4" H
Weight of a box	• 49 to 53 lbs	• 49 to 60 lbs	• 49 to 51 lbs
Content of a pallet	• 48 boxes = 960 ft <sup>2</sup> (4 boxes/W x 12 boxes/H)	• 48 boxes = 960 ft <sup>2</sup> (4 boxes/W x 12 boxes/H)	• 48 boxes = 864 ft <sup>2</sup> (4 boxes/W x 12 boxes/H)
Size of a pallet	• 86" L x 38" W x 43" H	• 79" L x 42" W x 43" H	• 82" L x 38" W x 43" H
Relative species hardness			
NWFA Janka Test	• American Walnut	1,010 lbs - 22% softer	
Hardness test (ASTM-D-143)	• Yellow Birch	1,260 lbs - 2% softer	
	• Red Oak	1,290 lbs - average hardness	
Red Oak 1290 lbs* - 100%	• Maple	1,450 lbs - 12% harder	
*lbs = Applied force in pounds			

\* Cashmere is a registered trademark used under license.