



Characteristics	Mirage Classic								
Description	<ul style="list-style-type: none"> <li>• For Admiration, Natural, Flair, Sweet Memories and Imagine Collections</li> <li>• Solid prefinished hardwood flooring with tongues and grooves</li> <li>• Micro-V bevel (on 4 sides)</li> </ul>								
Thickness	3/4"								
Width	2-1/4"	3-1/4"	4-1/4"						
Length	Random lengths from 10" to 76"								
Installation	Nailed or stapled down (above and on grade)								
Subfloor	Wood								
Species	4 species: Maple, Red Oak, White Oak and Yellow Birch.								
Grade	<ul style="list-style-type: none"> <li>• <b>Select &amp; Better:</b> Selection of more uniform wood grain with slight variations in natural shading</li> <li>• <b>Exclusive:</b> Wood planks with some pronounced and nuanced coloration. The Exclusive grade offers a range of color variation.</li> <li>• <b>Character floors:</b> These floors are appreciated for their pronounced color variation. They feature open and closed knots, mineral streaks, cracks, surface holes, and other character or milling marks. Some distinctive marks may become prominent over time due to changes in the environment.</li> </ul>								
Color choice (refer to 2019 Mirage Collections)	49 colors: Nordic, Greystone, Charcoal, Graphite, Isla, Cape Cod, Rio, Savanna, Rich Oak, Havana, Java, Coffee, Sierra, Golden, Nevada, Auburn, Canyon, Umbria, Vienna, Platinum, Natural, White Mist, Snowdrift, Sand Dune, Grey Drizzle, Lunar Eclipse, Nightfall, Bubble Bath, Hula Hoop, Carousel, Sand Castle, Château, Roller Coaster, Gelato, Treasure, Peppermint, Hopscotch, Nougat, Tree House, Praline, Gingerbread, Black Jelly Bean, Driftwood, Rock Cliff, Barn Wood, Papyrus, Seashell, Sandstone, Fossil. Some products may not be available. Ask your Mirage representative or consult the product chart.								
Finish	<ul style="list-style-type: none"> <li>• <b>DuraMatt™:</b> Finishing system made of aluminum oxide and nanosilica particle composites suspended in UV cured polyurethane.</li> <li>• <b>Nanolinx™ HD:</b> Finishing system made of aluminum oxide and nanosilica particle composites suspended in UV cured polyurethane.                             <ul style="list-style-type: none"> <li>• <b>Semi-gloss (50% gloss) or Cashmere®* (18% gloss)</b></li> </ul> </li> <li>• <b>Nanolinx™ Commercial:</b> Ultraresistant finishing system made of aluminum oxide and nanosilica particle composites suspended in UV cured polyurethane.</li> </ul> UV Protection: All products Static Friction Coefficient (ASTM-D-2047): Slippery resistance of 0.5 to 0.55								
Applicable standards	<table border="0"> <tr> <td> <b>Surface Burning (ASTM-E-84):</b>                              • FSI (Flame Spread Index) 100 to 150                              Classe C (depends on wood species)                              • SD (Smoke Development) 75 to 400 (depends on wood species)                         </td> <td> <b>Surface Burning (ULC-S-102-2):</b>                              • FSV (Flame Spread Value) 100 to 150 (depends on wood species)                              • SD (Smoke Development) 200 to 300 (depends on wood species)                         </td> </tr> <tr> <td> <b>Critical radiant flux (ASTM-E-648-94a):</b>                              0.25 to 0.40 watt/cm<sup>2</sup> (depends on wood species)                         </td> <td> <b>R value:</b> R 0.6 to 0.8 (depends on wood species)                         </td> </tr> <tr> <td colspan="2"> <b>Formaldehyde and VOC emissions (CDPH 1.1, 2010) :</b> Target product group (Classic) conform                         </td> </tr> </table>			<b>Surface Burning (ASTM-E-84):</b> • FSI (Flame Spread Index) 100 to 150 Classe C (depends on wood species) • SD (Smoke Development) 75 to 400 (depends on wood species)	<b>Surface Burning (ULC-S-102-2):</b> • FSV (Flame Spread Value) 100 to 150 (depends on wood species) • SD (Smoke Development) 200 to 300 (depends on wood species)	<b>Critical radiant flux (ASTM-E-648-94a):</b> 0.25 to 0.40 watt/cm <sup>2</sup> (depends on wood species)	<b>R value:</b> R 0.6 to 0.8 (depends on wood species)	<b>Formaldehyde and VOC emissions (CDPH 1.1, 2010) :</b> Target product group (Classic) conform	
<b>Surface Burning (ASTM-E-84):</b> • FSI (Flame Spread Index) 100 to 150 Classe C (depends on wood species) • SD (Smoke Development) 75 to 400 (depends on wood species)	<b>Surface Burning (ULC-S-102-2):</b> • FSV (Flame Spread Value) 100 to 150 (depends on wood species) • SD (Smoke Development) 200 to 300 (depends on wood species)								
<b>Critical radiant flux (ASTM-E-648-94a):</b> 0.25 to 0.40 watt/cm <sup>2</sup> (depends on wood species)	<b>R value:</b> R 0.6 to 0.8 (depends on wood species)								
<b>Formaldehyde and VOC emissions (CDPH 1.1, 2010) :</b> Target product group (Classic) conform									
Provenance	Made in St-Georges, Qc, Canada.								
Use	Residential, light commercial or commercial (Nanolinx™ Commercial)								
Accessory	Round Stair nosing, Square Stair nosing, Round Reducer, Multifunction reducer, Threshold, "T" molding, Quarter round								
Warranty	<table border="0"> <tr> <td> <ul style="list-style-type: none"> <li>• Structural <b>lifetime</b> limited warranty (Relative humidity must always be maintained within a range of 35% and 55%).</li> </ul> </td> <td> <ul style="list-style-type: none"> <li>• <b>35-year</b> finish warranty for residential applications</li> <li>• <b>3-year</b> finish warranty for light commercial applications</li> <li>• <b>5-year</b> finish warranty for commercial applications with Nanolinx™ Commercial</li> </ul> </td> </tr> </table>			<ul style="list-style-type: none"> <li>• Structural <b>lifetime</b> limited warranty (Relative humidity must always be maintained within a range of 35% and 55%).</li> </ul>	<ul style="list-style-type: none"> <li>• <b>35-year</b> finish warranty for residential applications</li> <li>• <b>3-year</b> finish warranty for light commercial applications</li> <li>• <b>5-year</b> finish warranty for commercial applications with Nanolinx™ Commercial</li> </ul>				
<ul style="list-style-type: none"> <li>• Structural <b>lifetime</b> limited warranty (Relative humidity must always be maintained within a range of 35% and 55%).</li> </ul>	<ul style="list-style-type: none"> <li>• <b>35-year</b> finish warranty for residential applications</li> <li>• <b>3-year</b> finish warranty for light commercial applications</li> <li>• <b>5-year</b> finish warranty for commercial applications with Nanolinx™ Commercial</li> </ul>								
Packaging	2-1/4"	3-1/4"	4-1/4"						
Content of a box	• 20 ft <sup>2</sup>	• 20 ft <sup>2</sup>	• 18 ft <sup>2</sup>						
Size of a box	• 86" L x 9-1/2" W x 3-1/4" H	• 79" L x 10-1/2" W x 3-1/4" H	• 85-1/2" L x 9" W x 3-1/4" H						
Weight of a box	• 49 to 60 lbs	• 49 to 60 lbs	• 45 to 55 lbs						
Content of a pallet	• 48 boxes = 960 ft <sup>2</sup> (4 boxes/W x 12 boxes/H)	• 48 boxes = 960 ft <sup>2</sup> (4 boxes/W x 12 boxes/H)	• 48 boxes = 864 ft <sup>2</sup> (4 boxes/W x 12 boxes/H)						
Size of a pallet	• 86" L x 38" W x 42" H	• 79" L x 42" W x 42" H	• 85-1/2" L x 37" W x 42" H						
Relative species hardness	<table border="0"> <tr> <td>                     • Yellow Birch                      • Red Oak                      • White Oak                      • Maple                 </td> <td>                     1,260 lbs - 2% softer                      1,290 lbs - average hardness                      1,360 lbs - 5% harder                      1,450 lbs - 12% harder                 </td> </tr> </table>			• Yellow Birch • Red Oak • White Oak • Maple	1,260 lbs - 2% softer 1,290 lbs - average hardness 1,360 lbs - 5% harder 1,450 lbs - 12% harder				
• Yellow Birch • Red Oak • White Oak • Maple	1,260 lbs - 2% softer 1,290 lbs - average hardness 1,360 lbs - 5% harder 1,450 lbs - 12% harder								
NWFA Janka Test	• Yellow Birch 1,260 lbs - 2% softer								
Hardness test (ASTM-D-143)	• Red Oak 1,290 lbs - average hardness								
Red Oak 1290 lbs* - 100%	• White Oak 1,360 lbs - 5% harder								
*lbs = Applied force in pounds	• Maple 1,450 lbs - 12% harder								

\* Cashmere is a registered trademark used under license.