



Characteristics	Mirage Classic							
Description	<ul style="list-style-type: none"> • For Admiration, Natural, Flair, Sweet Memories, Imagine and Escape Collections • Solid prefinished hardwood flooring with tongues and grooves • Micro-V bevel (on 4 sides) 							
Thickness	3/4"							
Width	3-1/4"	4-1/4"						
Length	Random lengths from 10" to 76"							
Installation	Nailed or stapled down (above and on grade)							
Subfloor	Wood							
Species	4 species: Maple, Red Oak, White Oak, Yellow Birch							
Grade	<ul style="list-style-type: none"> • Select & Better: Selection of more uniform wood grain with slight variations in natural shading • Exclusive: Wood planks with some pronounced and nuanced coloration. The Exclusive grade offers a range of color variation. • Character floors: These floors are appreciated for their pronounced color variation. They feature open and closed knots, mineral streaks, cracks, surface holes, and other character or milling marks. Some distinctive marks may become prominent over time due to changes in the environment. 							
Color choice (refer to 2020 Mirage Collections)	52 colors: Auburn, Black Jelly Bean, Bubble Bath, Canyon, Cape Cod, Carmel, Carousel, Charcoal, Château, Coffee, Cold Springs, Destin, Driftwood, Gelato, Gingerbread, Golden, Greystone, Graphite, Grey Drizzle, Havana, Hopscotch, Hula Hoop, Isla, Laguna, Lunar Eclipse, Mystic Island, Natural, Nevada, New Haven, Nightfall, Nordic, Nougat, Papyrus, Peppermint, Platinum, Praline, Providence, Rich Oak, Rio, Rock Cliff, Roller Coaster, Sand Castle, Sandstone, Savanna, Sierra, Snowdrift, Stillwater Treasure, Tree House, Umbria, Vienna, White Mist. Some products may not be available. Ask your Mirage representative or consult the product chart.							
Finish	<ul style="list-style-type: none"> • DuraMatt®: Finishing system made of aluminum oxide and nanosilica particle composites suspended in UV cured polyurethane. • Nanolinx® HD: Finishing system made of aluminum oxide and nanosilica particle composites suspended in UV cured polyurethane. <ul style="list-style-type: none"> • Semi-gloss (50% gloss) or Cashmere®* (18% gloss) • Nanolinx® Commercial: Ultraresistant finishing system made of aluminum oxide and nanosilica particle composites suspended in UV cured polyurethane. UV Protection: All products Static Friction Coefficient (ASTM-D-2047): Slippery resistance of 0.5 to 0.55							
Applicable standards	<table border="0"> <tr> <td> Surface Burning (ASTM-E-84): • FSI (Flame Spread Index) 100 to 150 Class C (depends on wood species) • SD (Smoke Development) 75 to 400 (depends on wood species) </td> <td> Surface Burning (ULC-S-102-2): • FSV (Flame Spread Value) 100 to 150 (depends on wood species) • SD (Smoke Development) 200 to 300 (depends on wood species) </td> </tr> <tr> <td> Critical radiant flux (ASTM-E-648-94a): 0.25 to 0.40 watt/cm² (depends on wood species) </td> <td> R value: R 0.6 to 0.8 (depends on wood species) </td> </tr> <tr> <td colspan="2"> Formaldehyde and VOC emissions (CDPH 1.1, 2010) : Target product group (Classic) conform </td> </tr> </table>		Surface Burning (ASTM-E-84): • FSI (Flame Spread Index) 100 to 150 Class C (depends on wood species) • SD (Smoke Development) 75 to 400 (depends on wood species)	Surface Burning (ULC-S-102-2): • FSV (Flame Spread Value) 100 to 150 (depends on wood species) • SD (Smoke Development) 200 to 300 (depends on wood species)	Critical radiant flux (ASTM-E-648-94a): 0.25 to 0.40 watt/cm ² (depends on wood species)	R value: R 0.6 to 0.8 (depends on wood species)	Formaldehyde and VOC emissions (CDPH 1.1, 2010) : Target product group (Classic) conform	
Surface Burning (ASTM-E-84): • FSI (Flame Spread Index) 100 to 150 Class C (depends on wood species) • SD (Smoke Development) 75 to 400 (depends on wood species)	Surface Burning (ULC-S-102-2): • FSV (Flame Spread Value) 100 to 150 (depends on wood species) • SD (Smoke Development) 200 to 300 (depends on wood species)							
Critical radiant flux (ASTM-E-648-94a): 0.25 to 0.40 watt/cm ² (depends on wood species)	R value: R 0.6 to 0.8 (depends on wood species)							
Formaldehyde and VOC emissions (CDPH 1.1, 2010) : Target product group (Classic) conform								
Provenance	Made in St-Georges, Qc, Canada.							
Use	Residential, light commercial or commercial (Nanolinx® Commercial)							
Accessory	Round Stair nosing, Square Stair nosing, Round Reducer, Multifunction reducer, Threshold, "T" molding, Quarter round							
Warranty	<table border="0"> <tr> <td> <ul style="list-style-type: none"> • Structural lifetime limited warranty (Relative humidity must always be maintained within a range of 35% and 55%). </td> <td> <ul style="list-style-type: none"> • 35-year finish warranty for residential applications • 3-year finish warranty for light commercial applications • 5-year finish warranty for commercial applications with Nanolinx® Commercial </td> </tr> </table>		<ul style="list-style-type: none"> • Structural lifetime limited warranty (Relative humidity must always be maintained within a range of 35% and 55%). 	<ul style="list-style-type: none"> • 35-year finish warranty for residential applications • 3-year finish warranty for light commercial applications • 5-year finish warranty for commercial applications with Nanolinx® Commercial 				
<ul style="list-style-type: none"> • Structural lifetime limited warranty (Relative humidity must always be maintained within a range of 35% and 55%). 	<ul style="list-style-type: none"> • 35-year finish warranty for residential applications • 3-year finish warranty for light commercial applications • 5-year finish warranty for commercial applications with Nanolinx® Commercial 							
Packaging	3-1/4"	4-1/4"						
Content of a box	• 20 sq. ft.							
Size of a box	• 79" L x 10-1/2" W x 3-1/4" H							
Weight of a box	• 49 to 60 lbs							
Content of a pallet	• 48 boxes = 960 sq. ft. (4 boxes/W x 12 boxes/H)							
Size of a pallet	• 79" L x 42" W x 42" H							
Relative species hardness								
NWFA Janka Test	• Yellow Birch	1,260 lbs - 2% softer						
Hardness test (ASTM-D-143)	• Red Oak	1,290 lbs - average hardness						
	• White Oak	1,360 lbs - 5% harder						
Red Oak 1290 lbs* - 100%	• Maple	1,450 lbs - 12% harder						
*lbs = Applied force in pounds								

* Cashmere is a registered trademark used under license.