



Characteristics	Mirage Classic			
	Imagine Collection			
Description	<ul style="list-style-type: none"> • Solid prefinished hardwood flooring with tongues and grooves • Micro-V bevel (on 4 sides) • Textured 			
Thickness	3/4" (19 mm)			
Length	• Random lengths (from 10" (250 mm) to 76" (1,930 mm))			
Width	3-1/4" (83 mm)	4-1/4" (108 mm)		
Species	2 species: Red Oak Character, Maple Character			
Grade	<ul style="list-style-type: none"> • Character-looking floors: These floors are appreciated for their pronounced color variation. They feature open and closed knots, mineral streaks, cracks, surface holes, and other character or milling marks. Some distinctive marks may become prominent over time due to changes in the environment. 			
Color choice (refer to 2017 Mirage Collections)	7 colors (Red Oak): Papyrus, Driftwood, Rock Cliff, Sandstone, Seashell, Barn Wood, Fossil 4 colors (Maple): Papyrus, Driftwood, Rock Cliff, Sandstone			
Finish	<ul style="list-style-type: none"> • Nanolinx HD™: Finishing system made of aluminum oxide and nanosilica particle composites suspended in UV cured polyurethane. • Cashmere®* (18% gloss) • DuraMatt™: Finishing system made of aluminum oxide and nanosilica particle composites suspended in UV cured polyurethane. UV Protection: All products Formaldehyde: Free Water and solvent: No trace Static Friction Coefficient (ASTM-D-2047): Slippery resistance of 0.5 to 0.55			
Applicable standards	<table border="0" style="width: 100%;"> <tr> <td style="width: 50%; vertical-align: top;"> Surface Burning (ASTM-E-84): • FSI (Flame Spread Index) 100 to 150 Classe C (depends on wood species) • SD (Smoke Development) 75 to 400 (depends on wood species) Critical radiant flux (ASTM-E-648-94a): 0.25 to 0.40 watt/cm² (depends on wood species) Formaldehyde and VOC emissions (CDPH 1.1, 2010) : Target product group (Classic) conform </td> <td style="width: 50%; vertical-align: top;"> Surface Burning (ULC-S-102-2): • FSV (Flame Spread Value) 100 to 150 (depends on wood species) • SD (Smoke Development) 200 to 300 (depends on wood species) R value: R 0.6 to 0.8 (depends on wood species) </td> </tr> </table>		Surface Burning (ASTM-E-84): • FSI (Flame Spread Index) 100 to 150 Classe C (depends on wood species) • SD (Smoke Development) 75 to 400 (depends on wood species) Critical radiant flux (ASTM-E-648-94a): 0.25 to 0.40 watt/cm ² (depends on wood species) Formaldehyde and VOC emissions (CDPH 1.1, 2010) : Target product group (Classic) conform	Surface Burning (ULC-S-102-2): • FSV (Flame Spread Value) 100 to 150 (depends on wood species) • SD (Smoke Development) 200 to 300 (depends on wood species) R value: R 0.6 to 0.8 (depends on wood species)
Surface Burning (ASTM-E-84): • FSI (Flame Spread Index) 100 to 150 Classe C (depends on wood species) • SD (Smoke Development) 75 to 400 (depends on wood species) Critical radiant flux (ASTM-E-648-94a): 0.25 to 0.40 watt/cm ² (depends on wood species) Formaldehyde and VOC emissions (CDPH 1.1, 2010) : Target product group (Classic) conform	Surface Burning (ULC-S-102-2): • FSV (Flame Spread Value) 100 to 150 (depends on wood species) • SD (Smoke Development) 200 to 300 (depends on wood species) R value: R 0.6 to 0.8 (depends on wood species)			
Installation	Nailed or stapled down (above and on grade)			
Subfloor	Wood			
Provenance	Made in St-Georges, Qc, Canada.			
Use	Residential or light commercial			
Accessory	Textured square stair nosing, Round reducer, Multifunction reducer, Threshold, "T" molding, Quarter round			
Warranty	<ul style="list-style-type: none"> • Structural lifetime limited warranty • 35-year finish warranty for residential applications • 3-year finish warranty for light commercial applications 			
Packaging	3-1/4" (83 mm)	4-1/4" (108 mm)		
Content of a box	• 20 ft ² (1.858 m ²)			
Size of a box	• 79" L x 10-1/2" W x 3-1/4" H			
Weight of a box	• 49 to 60 lbs			
Content of a pallet	• 48 boxes = 960 ft ² (4 boxes/W x 12 boxes/H)			
Size of a pallet	• 79" L x 42" W x 43" H			
Relative species hardness				
NWFA Janka Test	• Red Oak	1,290 lbs - average hardness		
Hardness test (ASTM-D-143)	• Maple	1,450 lbs - 12% harder		
Red Oak 1290 lbs* - 100% *lbs = Applied force in pounds				

* Cashmere is a registered trademark used under license.