



Characteristics	Mirage Classic	
Description	<ul style="list-style-type: none"> <li>• Solid prefinished hardwood flooring with tongues and grooves</li> <li>• Micro-V bevel (on 4 sides)</li> </ul>	
Thickness	3/4"	
Width	3-1/4"	4-1/4"
Length <sup>1</sup>	Random lengths from 10" (250 mm) to 76" (1,930 mm)	
Installation	Nailed or stapled down (above and on grade)	
Subfloor	Wood	
Species	3 species: Maple, Red Oak, White Oak	
Grade	<ul style="list-style-type: none"> <li>• <b>Select &amp; Better:</b> Selection of more uniform wood grain with slight variations in natural shading.</li> <li>• <b>Exclusive:</b> Wood planks with some pronounced and nuanced coloration. The Exclusive grade offers a range of color variation.</li> <li>• <b>▲ Character:</b> These floors are appreciated for their pronounced color variation. They feature open and closed knots, mineral streaks, cracks, surface holes, and other character or milling marks. Some distinctive marks may become prominent over time due to changes in the environment.</li> </ul>	
Color choice (refer to 2023 Mirage Collections)	Some products may not be available. Ask your Mirage representative or consult the <a href="#">Product Chart</a> .	
Finish	Finishing system made of aluminum oxide and nanosilica particle composites suspended in UV cured polyurethane. <ul style="list-style-type: none"> <li>• DuraMatt® (5% gloss)</li> <li>• Nanolinx® HD                             <ul style="list-style-type: none"> <li>• Cashmere®* (18% gloss)</li> </ul> </li> <li>• Nanolinx® Commercial (18% gloss)</li> </ul> UV Protection: All products Static Friction Coefficient (ASTM-D-2047): Slippery resistance superior to 0.5	
Applicable standards	<b>Surface Burning (ASTM-E-84):</b> <ul style="list-style-type: none"> <li>• FSI (Flame Spread Index) 100 to 150 Class C (depends on wood species)</li> <li>• SD (Smoke Development) 75 to 400 (depends on wood species)</li> </ul> <b>Critical radiant flux (ASTM-E-648-94a):</b> 0.25 to 0.40 watt/cm <sup>2</sup> (depends on wood species)	<b>Surface Burning (ULC-S-102-2):</b> <ul style="list-style-type: none"> <li>• FSV (Flame Spread Value) 100 to 150 (depends on wood species)</li> <li>• SD (Smoke Development) 200 to 300 (depends on wood species)</li> </ul> <b>R value:</b> R 0.6 to 0.8 (depends on wood species)
	<b>Formaldehyde and VOC emissions (CDPH 1.2, 2017) :</b> Target product group (Classic) conform	
Provenance	Made in St-Georges, Qc, Canada.	
Use	Residential, light commercial or commercial (Nanolinx® Commercial)	
Accessory	Round Stair nosing, Square Stair nosing, Round Reducer, Threshold, "T" molding, Quarter round	
Warranty	<ul style="list-style-type: none"> <li>• Structural <b>lifetime</b> limited warranty (Relative humidity must always be maintained within a range of 35% and 55%).</li> </ul>	<ul style="list-style-type: none"> <li>• <b>35-year</b> finish warranty for residential applications</li> <li>• <b>3-year</b> finish warranty for light commercial applications</li> <li>• <b>5-year</b> finish warranty for commercial applications with Nanolinx® Commercial</li> </ul>
Packaging	3-1/4"	4-1/4"
Content of a box	• 20 sq. ft.	• 18 sq. ft.
Size of a box	• 79" L x 10-1/2" W x 3-1/4" H	• 85-1/2" L x 9" W x 3-1/4" H
Weight of a box	• 49 to 60 lbs	• 45 to 55 lbs
Content of a pallet	• 48 boxes = 960 sq. ft. (4 boxes/W x 12 boxes/H)	• 48 boxes = 864 sq. ft. (4 boxes/W x 12 boxes/H)
Size of a pallet	• 79" L x 42" W x 42" H	• 85-1/2" L x 36" W x 42" H
Relative species hardness		
NWFA Janka Test	• Red Oak	1,290 lbs - average hardness
Hardness test (ASTM-D-143)	• White Oak	1,360 lbs - 5% harder
	• Maple	1,450 lbs - 12% harder
Red Oak 1290 lbs* - 100% *lbs = Applied force in pounds		

\* Cashmere is a registered trademark used under license.

1. Lengths in inches have been rounded to the nearest unit. Please refer to values in millimeters to get the exact planks length.