



Characteristics	Mirage Classic											
Description	<ul style="list-style-type: none"> For Admiration, Natural, Flair, Sweet Memories, Imagine and Escape Collections Solid prefinished hardwood flooring with tongues and grooves Micro-V bevel (on 4 sides) 											
Thickness	3/4" (19 mm)											
Width	2-1/4" (57 mm)	3-1/4" (83 mm)	4-1/4" (108 mm)									
Length	Random lengths from 10" (254 mm) to 76" (1,930 mm)											
Installation	Nailed or stapled down (above and on grade)											
Subfloor	Wood											
Species	3 species: Maple, Red Oak, White Oak											
Grade	<ul style="list-style-type: none"> Select & Better: Selection of more uniform wood grain with slight variations in natural shading Exclusive: Wood planks with some pronounced and nuanced coloration. The Exclusive grade offers a range of color variation. Character: These floors are appreciated for their pronounced color variation. They feature open and closed knots, mineral streaks, cracks, surface holes, and other character or milling marks. Some distinctive marks may become prominent over time due to changes in the environment. 											
Color choice (refer to 2021 Mirage Collections)	44 colors: Auburn, Black Jelly Bean, Canyon, Cape Cod, Carmel, Charcoal, Château, Coffee, Cold Springs, Destin, Driftwood, Gelato, Gingerbread, Golden, Greystone, Graphite, Havana, Hopscotch, Hudson, Laguna, Mystic Island, Natural, Nevada, New Haven, Nordic, North Hatley, Nougat, Paddle Ball, Papyrus, Park City, Peppermint, Platinum, Praline, Providence, Rio, Rock Cliff, Sandstone, Savanna, Sierra, Stillwater, Treasure, Tree House, Waterloo, White Mist. Some products may not be available. Ask your Mirage representative or consult the product chart.											
Finish	Finishing system made of aluminum oxide and nanosilica particle composites suspended in UV cured polyurethane. <ul style="list-style-type: none"> DuraMatt® (5% gloss) Nanolinx® HD Semi-gloss (50% gloss) or Cashmere®* (18% gloss) Nanolinx® Commercial (18% gloss): Ultraresistant finishing system made of aluminum oxide and nanosilica particle composites suspended in UV cured polyurethane. UV Protection: All products Static Friction Coefficient (ASTM-D-2047): Slippery resistance superior to 0.5											
Applicable standards	<table border="0"> <tr> <td> Surface Burning (ASTM-E-84): <ul style="list-style-type: none"> FSI (Flame Spread Index) 100 to 150 Class C (depends on wood species) SD (Smoke Development) 75 to 400 (depends on wood species) </td> <td> Surface Burning (ULC-S-102-2): <ul style="list-style-type: none"> FSV (Flame Spread Value) 100 to 150 (depends on wood species) SD (Smoke Development) 200 to 300 (depends on wood species) </td> </tr> <tr> <td> Critical radiant flux (ASTM-E-648-94a): 0.25 to 0.40 watt/cm² (depends on wood species) </td> <td> R value: R 0.6 to 0.8 (depends on wood species) </td> </tr> <tr> <td colspan="2"> Formaldehyde and VOC emissions (CDPH 1.2, 2017) : Target product group (Classic) conform </td> </tr> </table>			Surface Burning (ASTM-E-84): <ul style="list-style-type: none"> FSI (Flame Spread Index) 100 to 150 Class C (depends on wood species) SD (Smoke Development) 75 to 400 (depends on wood species) 	Surface Burning (ULC-S-102-2): <ul style="list-style-type: none"> FSV (Flame Spread Value) 100 to 150 (depends on wood species) SD (Smoke Development) 200 to 300 (depends on wood species) 	Critical radiant flux (ASTM-E-648-94a): 0.25 to 0.40 watt/cm ² (depends on wood species)	R value: R 0.6 to 0.8 (depends on wood species)	Formaldehyde and VOC emissions (CDPH 1.2, 2017) : Target product group (Classic) conform				
Surface Burning (ASTM-E-84): <ul style="list-style-type: none"> FSI (Flame Spread Index) 100 to 150 Class C (depends on wood species) SD (Smoke Development) 75 to 400 (depends on wood species) 	Surface Burning (ULC-S-102-2): <ul style="list-style-type: none"> FSV (Flame Spread Value) 100 to 150 (depends on wood species) SD (Smoke Development) 200 to 300 (depends on wood species) 											
Critical radiant flux (ASTM-E-648-94a): 0.25 to 0.40 watt/cm ² (depends on wood species)	R value: R 0.6 to 0.8 (depends on wood species)											
Formaldehyde and VOC emissions (CDPH 1.2, 2017) : Target product group (Classic) conform												
Provenance	Made in St-Georges, Qc, Canada.											
Use	Residential, light commercial or commercial (Nanolinx® Commercial)											
Accessories	Round Stair nosing, Square Stair nosing, Round reducer, Multifunction reducer, Threshold, "T" molding, Quarter round											
Warranty	<ul style="list-style-type: none"> Structural lifetime limited warranty (Relative humidity must always be maintained within a range of 35% and 55%). 35-year finish warranty for residential applications 3-year finish warranty for light commercial applications 5-year finish warranty for commercial applications with Nanolinx® Commercial 											
Packaging	2-1/4" (57 mm)	3-1/4" (83 mm)	4-1/4" (108 mm)									
Content of a box	• 20 sq. ft. (1,858 m ²)	• 20 sq. ft. (1,858 m ²)	• 18 sq. ft. (1,672 m ²)									
Size of a box	• 86" L x 9-1/2" W x 3-1/4" H	• 79" L x 10-1/2" W x 3-1/4" H	• 85-1/2" L x 9" W x 3-1/4" H									
Weight of a box	• 49 to 60 lbs	• 49 to 60 lbs	• 45 to 55 lbs									
Content of a pallet	• 48 boxes = 960 sq. ft. (4 boxes/W x 12 boxes/H)	• 48 boxes = 960 sq. ft. (4 boxes/W x 12 boxes/H)	• 48 boxes = 864 sq. ft. (4 boxes/W x 12 boxes/H)									
Size of a pallet	• 86" L x 38" W x 42" H	• 79" L x 42" W x 42" H	• 85-1/2" L x 37" W x 42" H									
Relative species hardness	<table border="0"> <tr> <td>NWFA Janka Test</td> <td>• Red Oak</td> <td>1,290 lbs - average hardness</td> </tr> <tr> <td>Hardness test (ASTM-D-143)</td> <td>• White Oak</td> <td>1,360 lbs - 5% harder</td> </tr> <tr> <td></td> <td>• Maple</td> <td>1,450 lbs - 12% harder</td> </tr> </table> Red Oak 1,290 lbs* - 100% *lbs = Applied force in pounds			NWFA Janka Test	• Red Oak	1,290 lbs - average hardness	Hardness test (ASTM-D-143)	• White Oak	1,360 lbs - 5% harder		• Maple	1,450 lbs - 12% harder
NWFA Janka Test	• Red Oak	1,290 lbs - average hardness										
Hardness test (ASTM-D-143)	• White Oak	1,360 lbs - 5% harder										
	• Maple	1,450 lbs - 12% harder										

* Cashmere is a registered trademark used under license.