



Issued: January 21, 2009  
 Revised: January 31, 2011

# Technical Newsletter #23 1.1

## RE: Minimum criteria regarding adhesives for use with Mirage Engineered Flooring

The goal of this technical newsletter is to review the minimum requirements for ensuring the long term performance of adhesives used with Mirage Engineered floors.

Users are responsible for ensuring that the adhesive they select meets the requirements mentioned below. Mirage cannot be held responsible and makes no guarantees whatsoever with regards to:

1. The consistency of the adhesive's properties
2. The adhesive's chemical composition [VOCs, formaldehyde, or other products]
3. Problems with adhesive application or cleaning
4. The adhesive company's claim management process

When you select an adhesive, the manufacturer must guarantee in writing that the adhesive meets all the minimum criteria recommended by Mirage. The adhesive manufacturer must also assume sole responsibility for meeting all criteria mentioned in this document.

Warranty exclusions will include any flooring deficiencies stemming from the application method or the adhesive itself, as adhesives can damage the finish under certain conditions.

Choosing the right adhesive is a critical step in ensuring the long term integrity of Engineered flooring installation.

Mirage Engineered			
Criteria	Standard	Specification	Benefit if criteria is met
<b>Water content</b>		0%	To avoid water damage and not compromise installation
<input type="radio"/> <b>Green grab</b>		Holds ridges High initial grab	To hold product on uneven subfloor To facilitate installation, avoid floor/board misalignment
<input type="checkbox"/> <b>Shear strength</b>	<b>EN 14293</b>	72 psi [0.5 Mpa]	To ensure good bonding and performance
<input type="checkbox"/> <b>Elongation at break</b>	<b>EN 14293</b> [modified]	Between 40 and 400%	To allow appropriate expansion
<input type="checkbox"/> <b>Tensile strength</b>	<b>EN 14293</b>	90 psi [0.6 Mpa]	To ensure good bonding and performance
or			
<input type="checkbox"/> <b>Tensile strength</b>	<b>ASTM D-412</b> [method a]	72 psi [0.5 Mpa] [7 day cure]	To ensure good bonding and performance
<input type="checkbox"/> <b>Elongation at break</b>	<b>ASTM D-412</b> [method a]	Between 40 and 400%	To allow appropriate expansion
<input type="checkbox"/> <b>Creep of an assembly* [tensile or shear]</b>	<b>EN 14293</b> [modified] lap shear equivalent standard	or Max. 1 mm elongation [at loading] 30 psi [0.2 Mpa] loading [30 min.] [7 day cured assembly]	To avoid buckling, excessive expansion, or performance problems To ensure <u>long term</u> performance/stress resistance
<b>Adhesive transfer</b>		> 80%	To ensure good bonding
<input type="radio"/> <b>Curing time</b>		Max. 24 hrs	Excessively long cure times can lead to installation issues
<b>Service temperature</b>		20 to 110°F [-6 to 43°C]	To sustain variable temperature and radiant heat systems
<b>Warranty</b>		Lifetime	To match Mirage warranty

= Affected installation [time required and/or ease of installation]

\*Assembly: typical floor and concrete assembly [or similar to concrete]

= Properties that have an impact on product performance [expansion, cupping]

Note: ASTM D-412 and EN 14293 do not necessarily correlate.

The following points can't be managed by Mirage but are critical when choosing an adhesive:

- Spread rate [adhesive consumption]
- Underlay compatibility
- Subfloor compatibility
- Warranty exclusions
- Concrete sealer system: meets 3 lb./1,000. sq. ft /24 hrs
- Resistance to moisture/alkalinity [in concrete]
- Sealer/adhesive compatibility [refer to manufacturers]

Dino Tremblay, Technical Department Manager 1-800-463-1303