

# General Specifications



Characteristics	Mirage TruBalance	
	Chevron	
Description	<ul style="list-style-type: none"> <li>Structured prefinished hardwood flooring</li> <li>Micro-V bevel (on 4 sides)</li> <li>Incomparable <b>tongue and groove</b> fit for remarkable uniformity</li> </ul>	
Thickness	3/4" (19 mm) (Real Hardwood Top Lamella 4 mm, Locally Sourced SPF Quarter Sawn* Core layer 13 mm and Wood Backing Veneer 2 mm)	
Width	5" (127 mm)	
Length <sup>1</sup>	Fixed 24-7/16" (620 mm)	
Installation	Glued down (above, on or below grade)	
Subfloor	Wood, concrete or radiant heat system	
Species	2 species: White Oak, Oak	
Grade	<ul style="list-style-type: none"> <li><b>Exclusive:</b> Wood planks with some pronounced and nuanced coloration. The Exclusive grade offers a limited range of color variation.</li> <li><b>Character:</b> These floors are appreciated for their pronounced color variations. They feature open and closed knots, mineral streaks, surface holes, and other character or milling marks. Some distinctive marks may become prominent over time due to changes in the environment.</li> </ul>	
Color choice (refer to 2025 Mirage Collections)	Some products may not be available. Ask your Mirage representative or consult the <a href="#">Product Chart</a> .	
Finish	Finishing system made of aluminum oxide and nanosilica particle composites suspended in UV cured polyurethane. <ul style="list-style-type: none"> <li>DuraMatt® (5% gloss)</li> <li>DuraMatt® X (10% gloss)</li> <li>Nanolinx® Commercial (18% gloss)</li> </ul> UV Protection: All products Static Friction Coefficient (ASTM-D-2047): Slippery resistance superior to 0.5	
Applicable standards	Surface Burning (ASTM-E-84): <ul style="list-style-type: none"> <li>FSI (Flame Spread Index) 90 Class C</li> <li>SD (Smoke Development) 80</li> </ul> Critical radiant flux (ASTM-E-648-94a): 0.38 watt/cm <sup>2</sup> (depends on wood species)	Surface Burning (ULC-S-102-2): <ul style="list-style-type: none"> <li>FSR (Flame Spread Rating) 107</li> <li>SDC (Smoke Development Classification) 311</li> </ul> R value: R 0.86 to 0.89 (depends on wood species)
Provenance	Formaldehyde and VOC emissions (CDPH 1.2, 2017) : Target product group (TruBalance) conform Made in St-Georges, Qc, Canada.	
Use	Residential, light commercial or commercial	
Accessory	Round Stair Nosing, Square Stair Nosing, Matchable Square Stair Nosing, Round Reducer, Threshold, "T" Molding, Quarter Round, Wood Flush Mount Vent, Treads & Risers  Acoustitech underlayments are recommended by Mirage. To know more about the minimum criteria needed regarding the recommended waterproof acoustic underlayment, please refer to the <a href="#">Technical Newsletter #20</a> in the <a href="#">Guides and Support section</a> at <a href="http://miragefloors.com">miragefloors.com</a> .	
Warranty	<ul style="list-style-type: none"> <li>Structural <b>lifetime</b> limited warranty (Relative humidity must be maintained within a range of 25% and 80%).</li> </ul>	<ul style="list-style-type: none"> <li><b>35-year</b> finish warranty for residential applications</li> <li><b>3-year</b> finish warranty for light commercial applications</li> <li><b>5-year</b> finish warranty for commercial applications with Nanolinx® Commercial</li> </ul>
Recommended	For the installation of Chevron flooring, we recommend maintaining the relative humidity within a range of 35% and 70%. Staying in this range will ensure the pattern and overall look of your floor last over the years. For more information on the installation of Chevron flooring, consult the <a href="#">Installation Guide</a> .	
Patterns	<ul style="list-style-type: none"> <li>Chevron</li> <li>Spearhead</li> <li>Brooklyn Bridge</li> </ul>	<ul style="list-style-type: none"> <li>Leaf line</li> <li>Boardwalk</li> </ul>
Packaging	5" (127 mm)	
Content of a box	13.60 sq. ft.	
Size of a box	61-1/4" L x 10-1/2" W x 3-1/4" H	
Weight of a box	27 to 29 lb	
Content of a pallet	48 boxes = 652.80 sq. ft. (4 boxes/W x 12 boxes/H)	
Size of a pallet	61-1/4" L x 42-1/2" W x 41-1/2" H	
Relative species hardness		
NWFA Janka Test	White Oak	1,360 lbs - 5% harder
Hardness test (ASTM-D-143)	Oak	1,290 lbs - 5% average hardness
Red Oak 1,290 lbs* - 100%		
*lbs = Applied force in pounds		

\* Predominantly Quarter Sawn.

1. Values in inches have been rounded to the nearest unit. Please refer to values in millimeters to get the exact planks value.

Toll free : 1-800-463-1303